

Sipestar

Description:

Sipestar decorative multi-color wall finish very easy to use. For very fine touch finish with a high selected colors by one coat application. Sipestar multicolor based on vinyl synthetic copolymer with a very selected materials to improve performance and quality which is not available by use any other types of paints. Sipestar is alkaline resistant with low odor and good color resistance properties. Very easy to clean with excellent scratch resistance.

Areas Of Use:

Sipestar can be used to all surface interior and exterior its suitable for all surfaces, wood works, furniture cement, gypsum board, and all types of surface which requires a touch of decorative finish with a very nice colors collection. Sipestar is easy to use on all types of surfaces which is prepared by emulsion or alkyd paint base.

Specification Data:

Specific Gravity	1.01 ± Kg/L
Viscosity	1000 –2000 CP
Solid by volume	30 ±1%
Finish	Flat
Coverage	3-4 m ² / Kg due to condition of surface and tools of application
Drying time for touch	2 – 4 hours (Touch Dry)at 25C°
Drying time for Recoat	12 hours to recoat (Hard dry) at 25C°
Thinning	No thinning – No shaking
Washability	More than 5000 cycle
Mode of application	Air Spray Gun
Cleaning of tools	Using Sipes spirit
Flash point	Non flammable
Storage	2 years from date of production

Mode Of Application:

Apply by spray only, better if the gun is fitted with not less than 2.5mm nozzle. Set up provided with pressure pot or a fed gun with internal air mixing cup to obtain the proper thickness of the coating spreading.

Surfaces Preparation:

The surfaces should be dry, clean and free from contaminates such as grease, oil, dust, which can result in poor adhesion of the paint to the surface. Use a suitable solvent for cleaning, old flaking paint or poorly bound surfaces must be removed completely.

Wood Surfaces:

Surface should be treated by use Luxury Undercoat 313 after thinning, then allow the surface to dry then apply latex wall putty one coat.

Cement & Gypsum Surfaces:

Prime surface with Latex Sealer 1800 to fill the porasity of the surface. allow to dry, then apply two coats of Latex Wall Putty and use sanding paper for a very fine surface preparation.

Repainting Wood Surface:

Use a suitable sanding paper to release a flaking or loose painted surface and prepare the surface as in the beginning.

Cement And Gypsum Surfaces:

Clean the surface with water and soap, then wash it with fresh water to insure the surface clearance, then allow to dry.

Recommended Paint System:

In case of surface prepared by emulsion paint:

Product	No. of coats
Latex Sealer 1800	1
Wall putty	1
Si-Tone 700	1
Sipestar	1

In case of surface prepared by alkyd paint

Product	No. of coats
Wall Putty	1
Gold Crown Flat200	1
Sipestar	1

For Maximum Sipestar spreading rate, Si – Tone 700 or Gold Crown flat 200 with color closed to the base color selected on Sipestar

Safety For Use:

- 1- Keep away from direct sunlight with good ventilation.
- 2- Keep out of reach of children and direct flame.
- 3- Avoid eye contact and skin for a long time, if it happened, wash thoroughly with fresh water immediately.